

Single crystal EPR and ENDOR study of CsBr:Eu²⁺ in X and Q-band

F. Loncke*, H. Vrielinck, F. Callens and P. Matthys

*Ghent University, Department of Solid State Sciences,
Krijgslaan 281 – S1, B-9000 Gent, Belgium*

* Corresponding author : e-mail: Frank.Loncke@UGent.be, Tel. +32 9 264 43 51, Fax+32 9 264 49 96

Solids doped with rare earth ions are presently being used in numerous optical applications, e.g. laser crystals [1], dosimetric systems [2], etc. In various phosphor applications, as for electroluminescent flat screens [3] for optical or X-ray storage [4], Eu²⁺ is the optical dopant of choice.

In alkali halides with the NaCl-structure, Eu²⁺ has been investigated with Electron Paramagnetic Resonance (EPR) [5] and the existence of a vacancy-compensated Eu²⁺ centre has been demonstrated. However, hardly any EPR studies on Eu²⁺ have been reported for CsCl-type lattices.

For the present work we study Bridgman-grown CsBr:Eu single crystals, with EPR and Electron Nuclear Double Resonance (ENDOR) in X and Q-band (9.5 and 34 GHz). Before any treatment, no EPR signals are detected. After vacuum annealing at 500°C, signals of isolated Eu²⁺ ions can be recorded in the temperature range 10-60K. Interactions of the unpaired electrons with ¹³³Cs, ⁷⁹Br/⁸¹Br and ¹⁵¹Eu/¹⁵³Eu nuclei are identified in the ENDOR spectra.

Inspired by the work in the alkali halides with the rock salt structure, the possible aggregation behaviour of Eu²⁺-Vacancy dipoles is studied by in situ pulse annealing at temperatures up to room temperature.

[1] Guo H, Dong N, Yin M, Zhang WP, Lou LR and Xia SD, *J. Phys. Chem. B* 108 (50), 19205-19209 (2004)

[2] Coeck M, Vanhavere F and Khaidukov N, *Opt. Mat.* 26 (1), 65-70 (2004)

[3] Smet PF, Poelman D and Van Meirhaeghe RL, *J. Appl. Phys.* 95 (1), 184-190 (2004)

[4] S. Schweizer, *Phys. Stat. Sol (a)*, 187 (2), 335-393 (2001)

[5] G. Aguilar S., E. Munoz P., H. Murrieta S., L. A. Boatner and R.W. Reynolds, *J. Chem. Phys.* 60(12), 4665-4669 (1974)